

	Type	L #	Hits	Search Text	DBs	Time Stamp
1	BRS	L1	1196	fiber same epoxy same nylon same (glass or carbon)	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 12:39
2	BRS	L7	10	prepreg with nylon with (glass with carbon)	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 12:48
3	BRS	L13	22	polyester with matte with (glass or carbon)	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 12:47
4	BRS	L19	6	polyester with matte with (glass or carbon) with epoxy	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 12:48
5	BRS	L25	76	prepreg with polyester with (glass with carbon)	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 12:48
6	BRS	L31	0	prepreg with polyester with (glass with carbon)with matte	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 12:49

	Comments	Error Definition	Errors
1			0
2			0
3			0
4			0
5			0
6			0

	Type	L #	Hits	Search Text	DBs	Time Stamp
1	BRS	L1	3	prepreg with fiber with gradient	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 15:40
2	BRS	L7	20	prepreg same fiber same gradient	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 16:01
3	BRS	L13	87	epoxy same fiber same gradient	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 16:01
4	BRS	L19	21	epoxy with fiber with gradient	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 16:06
5	BRS	L25	6	epoxy with fiber with gradient with adhesive	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 16:41
6	BRS	L31	20	"3660140"	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 17:11

	Comments	Error Definition	Errors
1			0
2			0
3			0
4			0
5			0
6			0

	Type	L #	Hits	Search Text	DBs	Time Stamp
7	BRS	L37	25	structural adj adhesive adj film	USPAT; EPO; JPO; DERWEN T; IBM TDB	2001/10/12 17:12